



## TECHNICAL DATA SHEET - PETG Carbon Fiber

Raw Material Name: Polyethylene terephthalate glycol (PETG)  
 Application: Rotary Components  
 Manufacturer: Covalo Industries

### Material Specifications

Mechanical Property	Value	Unit	Test Method
Ultimate Tensile Strength	56	MPa	ISO 527-2
Tensile Modulus	5230	GPa	ISO 527-2
Strain at Break	3	%	ISO 527-2
Flexural Strength	80	MPa	ISO 178
Flexural Modulus	5740	MPa	ISO 178
Surface Resistance	>10 <sup>9</sup>	ohm/sq	ASTM D257
Specific Gravity	1.34	g/cm <sup>3</sup>	ISO 1183
Glass Transition Temperature	77	°C	DSC
HDT A @ .45 MPa	80	°C	ISO 75

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any